


Major Daniel STECH
EOARD
223/231 Old Marylebone Rd.
London NW1 5TH
UNITED KINGDOM

24 October 1995

Dear Major Stech,
please find enclosed a Final Report on a Research Contract SPC-94-4102
"Growth of GaSe Crystals". One can find in Report some physical para-
meters of grown crystals (15 items) with different thickness, required
by Contract.

Kind regards


Professor Kerim ALLAKHVERDIEV
Principle Investigator

Enclosure: Report on -3- pages
Figure of location of 15 crystals in 2boxes.

*Final report is acceptable -
Please make final payment.*

*J. Stech
12 Nov 95*

DTIC QUALITY INSPECTED 4

DISTRIBUTION STATEMENT A	
Approved for public release;	
Distribution Unlimited	

AG F 99-05-0861

REPORT DOCUMENTATION PAGE

Form Approved OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE 24 October 1995	3. REPORT TYPE AND DATES COVERED Final Report	
4. TITLE AND SUBTITLE Growth of GaSe Crystals			5. FUNDING NUMBERS F6170894W0774	
6. AUTHOR(S) Dr. G Brydon				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Qa Rel Associates Dunelm House 12 Favell Way Northampton NN3 3BZ United Kingdom			8. PERFORMING ORGANIZATION REPORT NUMBER N/A	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) EOARD PSC 802 BOX 14 FPO 09499-0200			10. SPONSORING/MONITORING AGENCY REPORT NUMBER SPC 94-4102	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.			12b. DISTRIBUTION CODE A	
13. ABSTRACT (Maximum 200 words) This report results from a contract tasking Qa Rel Associates as follows: Grow GaSe crystals as described in the attached proposal dated 1 August 1994. Samples should be single crystals of varying thickness with faces perpendicular to the c-axis. The samples should have nominal area of at least 10 x 10 mm.				
14. SUBJECT TERMS EOARD			15. NUMBER OF PAGES 3	
			16. PRICE CODE N/A	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

NSN 7540-01-280-5500

Standard Form 298 (Rev. 2-89)
Prescribed by ANSI Std. Z39-18
298-102

24 October 1995

FINAL REPORT ON A RESEARCH CONTRACT
SPC-94-4102 "GROWTH OF GaSe CRYSTALS"

According to the requirements of the Contract single crystals of layered compound GaSe (Gallium Selenide) were grown by modified Bridgman method. Characterization were made using the different techniques. Among them are:

DTA (Differential Thermal Analysis) of polycrystals
X-ray powder diffraction measurements
Optical characterization in polarized light
Electron scanning microscopy
Optical absorption in the range of the exciton
Transmission measurements in the spectral range 0.7-20 μm
Long wavelength far IR reflection in the reststrahlen bands
Raman scattering spectroscopy
Maker fringe pattern of SHG signal

The analysis showed that a content of grown crystals is close to stoichiometry. The position of exciton absorption ($n=1$) at 300 K at 620nm and at 4.2K at 587nm in accordance that the crystals belong predominantly to epsilon polytype (space group D_{3h}^1 , absence of the inversion symmetry, two layers per primitive unit cell). Simultaneous activity of the low-frequency rigid-layer mode E' (20cm^{-1}) in the IR and Raman scattering spectra (excited with 6471 \AA line of Kr-ion laser) also says in a favour of fact, that grown crystals belong to non-centrosymmetric epsilon modification(1).

Transmission measurements in the IR range showed, that all grown crystals are transparent in the region 0.7-18 μm , having absorption coefficient less than 1 cm^{-1} . Good optical quality of supplied crystals was also proved by measuring a Maker fringe pattern of the SHG signal excited in crystals with 1.579 μm line of Quanta-Ray RS-1 Raman Shifter (Spectra Physics) at room temperature. Observed fringes were clearly resolved and symmetric to "+" and "-" direction of rotation relative to optical C-axis.

19990204 001

Peak intensity damage at $10.6\mu\text{m}$ of CO_2 laser averaged for 5 crystals with thicknesses 5mm was about 30MWt/cm^2 at frequency repetition 20Hz.

One can summarize the physical properties of supplied crystals as follows:

Crystal structure:	space group $D_{3h}1$ ($P6m2$) $a=3.757\text{ \AA}$ $c=15.946\text{ \AA}$
Free carrier concentration:	$p \approx 8 \times 10^{14} \text{ cm}^{-3}$
Mobility:	$\mu \approx 30 \text{ cm}^2/\text{Vs}$
Transparency range:	$0.7-18\mu\text{m}$
Forbidden gap:	$E=2.020\text{eV}$
Position of the ground state of direct free excitons:	2.601eV
Direction of the optical C-axis:	always perpendicular to the cleavage plane
Peak intensity damage at $10.6\mu\text{m}$ of CO_2 laser at $f=20\text{Hz}$:	about 30MWt/cm^2
Nominal area available perpendicular to optical axis:	averaged for supplied crystals $13 \times 13\text{mm}$, not less than $10 \times 10\text{mm}$

Grown crystals are supplied in two different small boxes. They are numbered through 1 to 12 (see supplied figure). The crystals N1-4 are in a black thick box. The crystals N5-12 are in a thinner box. Number on top of each crystal is their weight in grams (for example 363660 for crystal N1 means 36.3660grams). Numbers inside-shows the thickness in mm.

The crystals numbered 1 and 2 are supposed to be cleaved each for two crystals:

N1 for crystal with $t=15\text{mm}$ and for crystal with $t=7\text{mm}$

N2 for crystal with $t=10\text{mm}$ and for crystal with $t=7\text{mm}$

Crystals N1 and N2 were not cleaved and lefted for decision and suitability of user, if they need the crystals with freshly cleaved surface or with thickness between 18 and 0.5mm.

But if we consider that N1 and N2 are cleaved, then the numbers on the left corner of figure shows the number (right row) and the thickness (in mm, left row) of supplied crystals. For example (6-1 means:

one crystal with thickness 6mm; 15-2 : two crystals with thickness 15mm

Taking into consideration such a classification all the crystals required by Contract are supplied:


1 with t=6mm	}	all can be attributed to the crystals with t=5mm
2 with t=7mm		
2 with t=8mm		
3 with t=10mm	}	all can be attributed to the crystals with t=10mm
2 with t=12mm		
1 with t=14mm	}	all can be attributed to the crystals with t=15mm
2 with t=15mm		
1 with t=18mm		

For each crystal thickness is shown in the direction of the optical axis C perpendicular to the cleavage surfaces with nominal area averaged 13x13mm and not less than 10x10mm, as stated in Contract.

Common weight of supplied crystals : 272.1843gramms.

REFERENCES:

1. Landolt-Burnstein, Zahlwerte und Funktionen aus Naturwissenschaften und Technik, Neu Serie Gesamtherausgabe: K. Hellwege, O. Modelung. Gruppe 3: Kristalle und Festkörperphysik. Band 17, Halbleiter, Springer, Berlin, Heidelberg, New York, Tokyo, 1983, p.530.
2. E. Salaev, K. Allakhverdiev "Dynamic and Static Nonlinear Effects in GaSe-Type Layer Crystals", Monography (in Russian), Elm, Baku 1993, p.231



Prof. Kerim ALLAKHVERDIEV
Principle Investigator

10	11	12
5	6	7
8	9	

11 202869



5 164486



9 978975



12 222394



6 73969



10 617151



7 153223



8 116092



4	3	2	1
---	---	---	---

4 181861




Figure. Locations of GaSe crystals (15 items) supplied according to the research contract SPC-94-4102.

Crystals N1 and 2 is supposed to be cleaved each for 2 crystals with thickness 15 and 7 (N1) and 10 and 7 mm (N2). Detailed description is given in the Final report (3 pages).